

**DWI****DERMABIT**  
WATERPROOFING IND.

# Technical Data Sheet

## ECOGUM SP

APP MODIFIED BITUMINOUS MEMBRANE WITH 200 G/M2 POLYESTER

Tests Performed – As per ASTM	Procedure	Units	Tolerance	Value
Length		m	<-1%	10
Width		m	<-1%	1
Thickness	ASTM D5147	mm	-0.2mm	4.00
Penetration of Coating Mixture at 25 Deg C.	ASTM D5	dmm	mlv	12-20
Tensile Properties : Max Tensile Force-Long	ASTM D5147	N/50mm	-20%	840
-Trans	ASTM D5147	N/50mm	-20%	630
Tensile Properties : Elongation -Long	ASTM D5147	%	-15	45
-Trans	ASTM D5147	%	-15	45
Resistance to Tearing -Long	ASTM D5147	N	min	600
-Trans	ASTM D5147	N	min	450
Lap Joint Strength -Long	ASTM D5147	N/5cm	-20%	840
-Trans	ASTM D5147	N/5cm	-20%	630
Flexibility at Low Temperature *	ASTM D5147	C	min	0
Dimensional Stability at 80C -Long	ASTM D5147	%	mlv	-0.5
-Trans	ASTM D5147	%	mlv	-0.5
Water Absorption (n/a slate)	ASTM D5147	%	mlv	<0.15

Tests Performed – As per CE	Procedure	Units	Tolerance	Value
Visible Defects	EN 1850-1	No./m <sup>2</sup>	0	0
Length	EN 1848-1	m	<-1%	10
Width	EN 1848-1	m	<-1%	1.00
Straightness	EN 1848-1	mm	<20mm	Pass
Mass Per Unit Area	EN 1849-1	kg/m <sup>2</sup>	+/- 10%	4.70
Thickness	EN 1849-1	mm	-0.2mm	4.00
Water Tightness to Liquid Water	EN 1928-1	mlv	>60kPa	Pass
Tensile Properties : Max Tensile Force-Long	EN 12311-1	N/5cm	-20%	840
-Trans	EN 12311-1	N/5cm	-20%	630
Tensile Properties : Elongation -Long	EN 12311-1	%	-15	45
-Trans	EN 12311-1	%	-15	45
Resistance to Tearing (Nail Shank) -Long	EN 12310-1	N	min	190
-Trans	EN 12310-1	N	min	180
Shear Resistance of Joint -Long	EN 12317-1	N/5cm	-20%	840
-Trans	EN 12317-1	N/5cm	-20%	630
Resistance to Static Loading (method A)	EN 12730	kg	min	20
Resistance to Impact	EN 12691	mm	mlv	>300
Flexibility at Low Temperature *	EN 1109	C	min	0
Dimensional Stability -Long	EN1107-1	%	max	-0.5
Flow Resistance less than 2mm	EN1110	C	mlv	100
Reaction to Fire	EN 13501-1		Euroclass	F

\* Different cold flexibility values can be supplied to special order.