

ELASPHALT 4200 PBS

AN SBS TYPE MODIFIED BITUMINOUS MEMBRANE OF 4MM THICK WITH 200 GSM POLYESTER AS REINFORCEMENT WITH PLAIN FINISH

Tests Performed – As per ASTM	Procedure	Units	Tolerance	Value
Length		m	<-1%	10
Width		m	<-1%	1
Thickness	ASTM D5147	mm	-0.2mm	4.00
Softening Point (R&B) of Coating Mixture	ASTM D36	C	min	130
Tensile Properties : Max Tensile Force-Long	ASTM D5147	N/50mm	-20%	900
-Trans	ASTM D5147	N/50mm	-20%	750
Tensile Properties : Elongation	ASTM D5147	%	-15	45
-Long	ASTM D5147	%	-15	50
-Trans	ASTM D5147	%	-15	50
Resistance to Tearing	ASTM D5147	N	min	500
-Long	ASTM D5147	N	min	400
-Trans	ASTM D5147	N	min	400
Lap Joint Strength	ASTM D5147	N/5cm	-20%	900
-Long	ASTM D5147	N/5cm	-20%	750
-Trans	ASTM D5147	N/5cm	-20%	750
Flexibility at Low Temperature	ASTM D5147	C	min	-5
Dimensional Stability at 80C	ASTM D5147	%	mlv	-0.5
-Long	ASTM D5147	%	mlv	-0.5
-Trans	ASTM D5147	%	mlv	-0.5
Water Absorption (n/a slate)	ASTM D5147	%	mlv	<0.15

Tests Performed – As per CE	Procedure	Units	Tolerance	Value
Visible Defects	EN 1850-1	No./m ²	0	0
Length	EN 1848-1	m	<-1%	10
Width	EN 1848-1	m	<-1%	1
Straightness	EN 1848-1	mm	<20mm	Pass
Mass Per Unit Area	EN 1849-1	kg/m ²	+/- 10%	4.7
Thickness	EN 1849-1	mm	-0.2mm	4.0
Water Tightness to Liquid Water Method B	EN 1928-1	mlv	>400kPa	Pass
Tensile Properties : Max Tensile Force-Long	EN 12311-1	N/5cm	-20%	900
-Trans	EN 12311-1	N/5cm	-20%	750
Tensile Properties : Elongation	EN 12311-1	%	-15	45
-Long	EN 12311-1	%	-15	50
-Trans	EN 12311-1	%	-15	50
Resistance to Tearing (Nail Shank)	EN 12310-1	N	min	220
-Long	EN 12310-1	N	min	240
-Trans	EN 12310-1	N	min	240
Shear Resistance of Joint	EN 12317-1	N/5cm	-20%	900
-Long	EN 12317-1	N/5cm	-20%	750
-Trans	EN 12317-1	N/5cm	-20%	750
Resistance to Static Loading (method A)	EN 12730	kg	min	25
Resistance to Impact	EN 12691	mm	mlv	>700
Flexibility at Low Temperature	EN 1109	C	min	-5
Dimensional Stability	EN1107-1	%	max	-0.5
-Long	EN1107-1	%	max	-0.5
Flow Resistance less than 2mm	EN1110	C	mlv	100
Reaction to Fire	EN 13501-1		Euroclass	F